

Material: ASTM B 574 N06210

Standard Specification for Low-Carbon Nickel-Chromium-Molybdenum, Alloy Rod

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 574 N06210 Low-Carbon Nickel-Chromium-Molybdenum, Alloy Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.015 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.080 max.		
Manganese	Mn %	0.500 max.		
Chromium	Cr %	18.000 - 20.000		
Sulphur	S %	0.020 max.		
Molybdenum	Mo %	18.000 - 20.000		
Phosphorus	P %	0.020 max.		
Cobalt	Co %	1.000 max.		
Iron	Fe %	1.000 max.		
Vanadium	V %	0.350 max.		
Tantalum	Ta %	1.500 - 2.200	Mechanical Properties Tensile Strength in Mpa 690 min. Yield Strength in Mpa 310 min. Elongation in % 45 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
Nickel	Ni %	Balance		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 564 N06210	ASTM	USA	Forging
B 575 N06210	ASTM	USA	Plate, Sheet and Strip
B 619 N06210	ASTM	USA	Pipe
B 622 N06210	ASTM	USA	Pipe and Tube
B 626 N06210	ASTM	USA	Tube
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com