

Material: ASTM B 574 N06686 Grade 1

Standard Specification for Low-Carbon Nickel-Chromium-Molybdenum Alloy Rod

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 574 N06686 Grade 1 Low-Carbon Nickel-Chromium-Molybdenum Alloy Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.080 max.		
Manganese	Mn %	0.750 max.		
Chromium	Cr %	19.000 - 23.000		
Sulphur	S %	0.020 max.		
Molybdenum	Mo %	15.000 - 17.000		
Phosphorus	P %	0.040 max.		
Tungsten	W %	3.000 - 4.400		
Iron	Fe %	5.000 max.		
Titanium	Ti %	0.020 - 0.250		
Nickel	Ni %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	690 min.
-	-	-	Yield Strength in Mpa	310 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 163 N06686	ASTM	USA	Tube
B 462 N06686	ASTM	USA	Pipe and Valve
B 564 N06686	ASTM	USA	Forging
B 575 N06686	ASTM	USA	Plate, Sheet and Strip
B 619 N06686	ASTM	USA	Pipe
B 622 N06686	ASTM	USA	Pipe and Tube
B 626 N06686	ASTM	USA	Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com