

Material: ASTM B 574 N10276

Standard Specification for Low-Carbon Nickel-Chromium-Molybdenum, Alloy Rod

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 574 N10276 Low-Carbon Nickel-Chromium-Molybdenum, Alloy Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.080 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	14.500 - 16.500		
Sulphur	S %	0.030 max.		
Molybdenum	Mo %	15.000 - 17.000		
Phosphorus	P %	0.040 max.		
Cobalt	Co %	2.500 max.		
Iron	Fe %	4.000 - 7.000		
Tungsten	W %	3.000 - 4.500		
Vanadium	V %	0.350 max.	Mechanical Properties Tensile Strength in Mpa 690 min. Yield Strength in Mpa 283 min. Elongation in % 40 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
Nickel	Ni %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 564 N10276	ASTM	USA	Forging
B 575 N10276	ASTM	USA	Plate, Sheet and Strip
B 462 N10276	ASTM	USA	Pipe Flanges, Forged Fittings, and Valve
B 619 N10276	ASTM	USA	Pipe
B 622 N10276	ASTM	USA	Pipe and Tube
B 626 N10276	ASTM	USA	Tube
N10276	UNS	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com