

Material: ASTM B 575 N06686

Standard Specification for Low-Carbon Nickel-Chromium-Molybdenum Alloy Plate, Sheet and Strip

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 575 N06686 Low-Carbon Nickel-Chromium-Molybdenum Alloy Plate, Sheet and Strip

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.080 max.		
Manganese	Mn %	0.750 max.		
Chromium	Cr %	19.000 - 23.000		
Sulphur	S %	0.020 max.		
Molybdenum	Mo %	15.000 - 17.000		
Phosphorus	P %	0.040 max.		
Titanium	Ti %	0.020 - 0.250		
Iron	Fe %	5.000 max.		
			Mechanical Properties	
Tungsten	W %	3.000 - 4.400	Tensile Strength in Mpa	690 min.
Nickel	Ni %	Balance	Yield Strength in Mpa	310 min.
-	-	-	Elongation in %	45 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRC	100 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 163 N06686	ASTM	USA	Tube
B 462 N06686	ASTM	USA	Pipe and Valve
B 564 N06686	ASTM	USA	Forging
B 574 N06686 Grade 1	ASTM	USA	Rod
B 619 N06686	ASTM	USA	Pipe
B 622 N06686	ASTM	USA	Pipe and Tube
B 626 N06686	ASTM	USA	Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com