

Material: ASTM B 619 N06007

Standard Specification for Nickel and Nickel-Cobalt Alloy Pipe

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 619 N06007 Nickel and Nickel-Cobalt Alloy Pipe

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Pipe

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 max.	As-Cast or Annealing or Age Hardening	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 - 2.000		
Chromium	Cr %	21.000 - 23.500		
Sulphur	S %	0.030 max.		
Molybdenum	Mo %	5.500 - 7.500		
Phosphorus	P %	0.040 max.		
Cobalt	Co %	2.500 max.		
Iron	Fe %	18.000 - 21.000	Mechanical Properties	
Copper	Cu %	1.500 - 2.500	Tensile Strength in Mpa	621 min.
Tungsten	W %	1.000 max.	Yield Strength in Mpa	241 min.
Nb + Ta	Nb% + Ta%	1.750 - 2.500	Elongation in %	35 min.
Nickel	Ni %	Balance	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 581 N06007	ASTM	USA	Rod
SB-581 N06007	ASME	USA	Rod
B 582 N06007	ASTM	USA	Plate, Sheet and Strip
B 622 N06007	ASTM	USA	Pipe and Tube
B 626 N06007	ASTM	USA	Tube
SB-619 N06007	ASME	USA	Pipe
SB-626 N06007	ASME	USA	Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com