

Material: ASTM B 619 N06210

Standard Specification for Nickel and Nickel-Cobalt Alloy Pipe

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 619 N06210 Nickel and Nickel-Cobalt Alloy Pipe

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Pipe

Chemical Composition			Heat Treatment	
Carbon	C %	0.015 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.080 max.		
Manganese	Mn %	0.500 max.		
Chromium	Cr %	18.000 - 20.000		
Sulphur	S %	0.020 max.		
Molybdenum	Mo %	18.000 - 20.000		
Phosphorus	P %	0.020 max.		
Cobalt	Co %	1.000 max.	Mechanical Properties Tensile Strength in Mpa 690 min. Yield Strength in Mpa 310 min. Elongation in % 45 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
Iron	Fe %	1.000 max.		
Vanadium	V %	0.350 max.		
Tantalum	Ta %	1.500 - 2.200		
Nickel	Ni %	Balance		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 564 N06210	ASTM	USA	Forging
B 574 N06210	ASTM	USA	Rod
B 575 N06210	ASTM	USA	Plate, Sheet and Strip
B 622 N06210	ASTM	USA	Pipe and Tube
B 626 N06210	ASTM	USA	Tube
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com