

Material: ASTM B 619 N06455

Standard Specification for Nickel and Nickel-Cobalt Alloy Pipe

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 619 N06455 Nickel and Nickel-Cobalt Alloy Pipe

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Pipe

Chemical Composition			Heat Treatment	
Carbon	C %	0.015 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.080 max.		
Manganese	Mn %	1.000 max.		
Cobalt	Co %	2.000 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	14.000 - 18.000		
Phosphorus	P %	0.040 max.		
Molybdenum	Mo %	14.000 - 17.000		
Iron	Fe %	3.000 max.		
Titanium	Ti %	0.700 max.		
Nickel	Ni %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	690 min.
-	-	-	Yield Strength in Mpa	276 min.
-	-	-	Elongation in %	40 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 574 N06455	ASTM	USA	Rod
B 575 N06455	ASTM	USA	Plate, Sheet and Strip
B 622 N06455	ASTM	USA	Pipe and Tube
B 626 N06455	ASTM	USA	Tube
SB-575 N06455	ASME	USA	Plate, Sheet and Strip
SB-619 N06455	ASME	USA	Pipe
SB-622 N06455	ASME	USA	Pipe and Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India