

Material: ASTM B 619 N08320

Standard Specification for Nickel and Nickel-Cobalt Alloy Pipe

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 619 N08320 Nickel and Nickel-Cobalt Alloy Pipe

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Pipe

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.500 max.		
Chromium	Cr %	21.000 - 23.000		
Sulphur	S %	0.030 max.		
Molybdenum	Mo %	4.000 - 6.000		
Phosphorus	P %	0.040 max.		
Titanium	Ti %	4 × C min.		
Nickel	Ni %	25.000 - 27.000		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	517 min.
-	-	-	Yield Strength in Mpa	193 min.
-	-	-	Elongation in %	35 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 622 N08320	ASTM	USA	Pipe and Tube
B 626 N08320	ASTM	USA	Tube
B 620 N08320	ASTM	USA	Plate, Sheet and Strip
B 621 N08320	ASTM	USA	Rod
SB-619 N08320	ASME	USA	Pipe
SB-620 N08320	ASME	USA	Plate, Sheet and Strip
SB-622 N08320	ASME	USA	Pipe and Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com