

Material: ASTM B 625 R20033

Standard Specification for Ni-Fe-Cr-Mo-Cu-N Low-Carbon Alloy, Plate, Sheet and Strip

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 625 R20033 Ni-Fe-Cr-Mo-Cu-N Low-Carbon Alloy, Plate, Sheet and Strip

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.015 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	2.000 max.		
Chromium	Cr %	31.000 - 35.000		
Sulphur	S %	0.010 max.		
Molybdenum	Mo %	0.500 - 2.000		
Phosphorus	P %	0.020 max.		
Nitrogen	N %	0.350 - 0.600		
Copper	Cu %	0.300 - 1.200	Mechanical Properties	
Nickel	Ni %	30.000 - 33.000	Tensile Strength in Mpa	750 min.
Iron	Fe %	Balance	Yield Strength in Mpa	380 min.
-	-	-	Elongation in %	40 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 564 R20033	ASTM	USA	Forging
B 649 R20033	ASTM	USA	Bar and Wire
B 462 R20033	ASTM	USA	Pipe Flanges, Forged Fittings and Valve
B 619 R20033	ASTM	USA	Pipe
B 622 R20033	ASTM	USA	Pipe and Tube
B 626 R20033	ASTM	USA	Tube
SB-649 R20033	ASME	USA	Bar and Wire

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com