

Material: ASTM B 626 N10276

Standard Specification for Nickel and Nickel-Cobalt Alloy Tube

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 626 N10276 Nickel and Nickel-Cobalt Alloy Tube

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Tube

Chemical Composition		
Carbon	C %	0.010 max.
Silicon	Si %	0.080 max.
Manganese	Mn %	1.000 max.
Cobalt	Co %	2.500 max.
Sulphur	S %	0.030 max.
Chromium	Cr %	14.500 - 16.500
Phosphorus	P %	0.040 max.
Molybdenum	Mo %	15.000 - 17.000
Iron	Fe %	4.000 - 7.000
Tungsten	W %	3.000 - 4.500
Vanadium	V %	0.350 max.
Nickel	Ni %	Balance
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast or Annealing or Age Hardning

Mechanical Properties	
Tensile Strength in Mpa	690 min.
Yield Strength in Mpa	283 min.
Elongation in %	40 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 564 N10276	ASTM	USA	Forging
B 574 N10276	ASTM	USA	Rod
B 575 N10276	ASTM	USA	Plate, Sheet and Strip
B 462 N10276	ASTM	USA	Pipe Flanges, Forged Fittings, and Valve
B 619 N10276	ASTM	USA	Pipe
B 622 N10276	ASTM	USA	Pipe and Tube
N10276	UNS	USA	Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com