

Material: ASTM B 704 N08825

Standard Specification for Nickel Alloy Tubes

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 704 N08825 Nickel Alloy Tubes

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.050 max.		
Manganese	Mn %	1.000 max.		
Copper	Cu %	1.500 - 3.000		
Sulphur	S %	0.030 max.		
Chromium	Cr %	19.500 - 23.500		
Aluminium	Al %	0.200 max.		
Molybdenum	Mo %	2.500 - 3.500		
Titanium	Ti %	0.600 - 1.200		
Iron	Fe %	22.000 max.		
Nickel	Ni %	38.000 - 46.000	Mechanical Properties Tensile Strength in Mpa 586 min. Yield Strength in Mpa 240 min. Elongation in % 30 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 163 N08825	ASTM	USA	Tube
B 423 N08825	ASTM	USA	Pipe and Tube
B 564 N08825	ASTM	USA	Forging
B 705 N08825	ASTM	USA	Pipe
SB-163 N08825	ASME	USA	Tube
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com