

Material: ASTM B 739 N08330

Standard Specification for Nickel-Iron-Chromium-Silicon Alloy Tube

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 739 N08330 Nickel-Iron-Chromium-Silicon Alloy Tube

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.750 - 1.500		
Manganese	Mn %	2.000 max.		
Chromium	Cr %	17.000 - 20.000		
Sulphur	S %	0.030 max.		
Lead	Pb %	0.005 max.		
Phosphorus	P %	0.030 max.		
Copper	Cu %	1.000 max.		
Tin	Sn %	0.025 max.		
Nickel	Ni %	34.000 - 37.000		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	483 min.
-	-	-	Yield Strength in Mpa	207 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRC	70 - 90
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 511 N08330	ASTM	USA	Bar and Shape
B 512 N08330	ASTM	USA	Billets and Bar
B 535 N08330	ASTM	USA	Pipe and Tube
B 536 N08330	ASTM	USA	Plate, Sheet and Strip
B 739 N08330	ASTM	USA	Tube
SB-511 N08330	ASME	USA	Bar and Shape
SB-535 N08330	ASME	USA	Pipe and Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com