

Material: ASTM B 759 N06110

Standard Specification for Nickel-Chromium-Molybdenum-Tungsten Alloys Pipe and Tube

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM B 759 N06110 Nickel-Chromium-Molybdenum-Tungsten Alloys Pipe and Tube

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Pipe and Tube

Chemical Composition		
Carbon	C %	0.150 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	1.000 max.
Chromium	Cr %	28.000 - 33.000
Sulphur	S %	0.015 max.
Molybdenum	Mo %	9.000 - 12.000
Phosphorus	P %	0.015 max.
Copper	Cu %	0.500 max.
Niobium	Nb %	1.000 max.
Tungsten	W %	1.000 - 4.000
Iron	Fe %	1.000 max.
Aluminium	Al %	1.000 max.
Titanium	Ti %	1.000 max.
Nickel	Ni %	51.000 min.
-	-	-

Heat Treatment
As-Cast or Annealing or Age Hardning

Mechanical Properties	
Tensile Strength in Mpa	655 min.
Yield Strength in Mpa	310 min.
Elongation in %	60 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 564 N06110	ASTM	USA	Forging
B 755 N06110	ASTM	USA	Plate, Sheet and Strip
B 756 N06110	ASTM	USA	Rod and Bar
B 757 N06110	ASTM	USA	Pipe
B 758 N06110	ASTM	USA	Tube
SB-564 N06110	ASME	USA	Forging
N06110	UNS	USA	Forging

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com