

Material: ASTM B271 High-Strength Yellow Brass UNS C86200

Standard Specification for Copper-Base Alloy Centrifugal Castings

Group: Non-Ferrous Copper Alloy

Sub Group: ASTM B271 Copper-Base Alloy Centrifugal Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Rod, Bar, Tube and Shapes

Chemical Composition			Heat Treatment	
Tin	Sn %	0.200 max.	As-Cast	
Lead	Pb %	0.200 max.		
Zinc	Zn %	22.000 - 28.000		
Iron	Fe %	2.000 - 4.000		
Ni + Co	Ni% + Co%	1.000 max.		
Aluminium	Al %	3.000 - 4.900		
Manganese	Mn %	2.500 - 5.000		
Copper	Cu %	60.000 - 66.000		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	621 min.
-	-	-	Yield Strength in Mpa	310 min.
-	-	-	Elongation in %	18 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B147-8B	ASTM	USA	Casting
B271 C86200	ASTM	USA	Casting
CA862	SAE	USA	Casting
SAE 430A	SAE	USA	Casting
SB-505 C86200	ASME	USA	Casting
SB-584 C86200	ASME	USA	Casting
CACIn303	KS	Korea	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com