

Material: ASTM B271 Nickel Alumium Bronze UNS C95500

Standard Specification for Copper-Base Alloy Centrifugal Castings

Group: Non-Ferrous Copper Alloy

Sub Group: ASTM B271 Copper-Base Alloy Centrifugal Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Rod, Bar, Tube and Shapes

Chemical Composition			Heat Treatment	
Iron	Fe %	3.000 - 5.500	As-Cast or Solution Annealing or Annealing or Normalizing	
Ni + Co	Ni% + Co%	3.000 - 5.500		
Aluminium	Al %	10.000 - 11.500		
Manganese	Mn %	3.500 max.		
Copper	Cu %	78.000 min.		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	620 min.
-	-	-	Yield Strength in Mpa	275 min.
-	-	-	Elongation in %	6 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	190 min.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B148 C95500	ASTM	USA	Casting
B30 C95500	ASTM	USA	Ingots and Casting
B271 C95500	ASTM	USA	Casting
SB-148 C95500	ASME	USA	Casting
SB-505 C95500	ASME	USA	Casting
CA955	SAE	USA	Casting
C95500	SAE	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com