

Material: ASTM B271 Nickel Alumium Bronze UNS C95520

Standard Specification for Copper-Base Alloy Centrifugal Castings

Group: Non-Ferrous Copper Alloy

Sub Group: ASTM B271 Copper-Base Alloy Centrifugal Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Rod, Bar, Tube and Shapes

Chemical Composition			Heat Treatment	
Tin	Sn %	0.250 max.	As-Cast or Solution Annealing or Annealing or Normalizing	
Lead	Pb %	0.030 max.		
Zinc	Zn %	0.300 max.		
Iron	Fe %	4.000 - 5.500		
Ni + Co	Ni% + Co%	4.200 - 6.000		
Aluminium	Al %	10.500 - 11.500		
Manganese	Mn %	1.500 max.		
Silicon	Si %	0.150 max.		
Copper	Cu %	74.500 min.		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B30 C95520	ASTM	USA	Ingot and Casting
B271 C95520	ASTM	USA	Casting
B505 C95520	ASTM	USA	Casting
SB-148 C95520	ASME	USA	Casting
78Cu-11Al-5.1Ni-4.8Fe	SAE	USA	Casting
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com