

Material: ASTM B30 C87800

Standard Specification for Copper Alloys Ingot and Casting

Group: Non-Ferrous Copper Alloy

Sub Group: ASTM B30 Copper Alloys Ingot and Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.150 max.	As-Cast	
Arsenic	As %	0.050 max.		
Iron	Fe %	0.150 max.		
Magnesium	Mg %	0.010 max.		
Manganese	Mn %	0.150 max.		
Ni + Co	Ni% + Co%	0.200 max.		
Phosphorus	P %	0.010 max.		
Lead	Pb %	0.090 max.		
Sulphur	S %	0.050 max.		
Antimony	Sb %	0.050 max.	Mechanical Properties	
Silicon	Si %	3.800 - 4.200	Tensile Strength in Mpa	586 min.
Tin	Sn %	0.250 max.	Yield Strength in Mpa	345 min.
Zinc	Zn %	12.000 - 16.000	Elongation in %	25 min.
Copper	Cu %	80 min.	Reduction of Area in %	-
-	-	-	Hardness in HRB	85 - 90
			Impact in Joule	95 min. @RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C87800	UNS	USA	Rod, Bar, Tube and Shapes
B176 C87800	ASTM	USA	Casting
CA878	SAE	USA	Casting
C87800	SAE	USA	Casting
C87800	UNS	USA	Casting
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com