

Material: ASTM B80 AZ92A

Standard Specification for Magnesium Alloy Sand Castings

Group: Non-Ferrous Magnesium Alloy

Sub Group: ASTM B80 Magnesium Alloy Sand Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	8.300 - 9.700	As-Cast or Solution Treated or Fully Treated	
Copper	Cu %	0.250 max.		
Manganese	Mn %	0.100 - 0.350		
Nickel	Ni %	0.010 max.		
Other	Ot%	0.300 max.		
Silicon	Si %	0.300 max.		
Zinc	Zn %	1.600 - 2.400		
Magnesium	Mg %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 158 - 234 Yield Strength in Mpa 76 - 124 Elongation in % 1 - 6 Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Mg-Al9Zn2	ISO	International	Bar and Wire
MC3	JIS	Japan	Casting
B93 AZ92A	ASTM	USA	Casting
B199 AZ92A	ASTM	USA	Casting
B275 AZ92A	ASTM	USA	Casting
B403 AZ92A	ASTM	USA	Casting
B951 AZ92A	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com