

Material: ASTM B86 AC41A

Standard Specification for Zinc and Zinc-Aluminum (ZA) Alloy Foundry and Die Castings

Group: Non-Ferrous Zinc Alloy

Sub Group: ASTM B86 Zinc and Zinc-Aluminum (ZA) Alloy Foundry and Die Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	3.700 - 4.300	As-Cast or Aging	
Cadmium	Cd %	0.004 max.		
Chromium	Cr %	0.020 max.		
Copper	Cu %	0.700 - 1.200		
Iron	Fe %	0.050 max.		
Magnesium	Mg %	0.020 - 0.060		
Manganese	Mn %	0.060 max.		
Nickel	Ni %	0.020 max.		
Lead	Pb %	0.005 max.		
Silicon	Si %	0.035 max.		
Tin	Sn %	0.002 max.	Mechanical Properties Tensile Strength in Mpa 328 min. Yield Strength in Mpa 228 min. Elongation in % 7 min. Reduction of Area in % - Hardness in HB 91 min. Impact in Joule 65 min. @RT	
Titanium	Ti %	0.001 max.		
Zinc	Zn %	Balance		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Zamak 5	ANSI/AA	USA	Casting
ZP5	ISO	International	Casting
Z33531	UNS	USA	Ingot and Casting
B86 Alloy 5	ASTM	USA	Casting
B86 Zamak 5	ASTM	USA	Casting
B240 AC41A	ASTM	USA	Ingot and Casting
B240 Zamak 5	ASTM	USA	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com