

Material: BS 10216-5 EN 1.4311

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: BS 10216-5 Seamless Steel Tubes for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	17.000 - 19.500		
Nickel	Ni %	8.500 - 11.500		
Nitrogen	N %	0.120 - 0.220		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 550 - 760 Yield Strength in Mpa 270 min. Elongation in % 30 min. Reduction of Area in % - Hardness in BHN - Impact in Joule 60 min. @ -196°C	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4311	DIN	Germany	Steel
1.4311	EN	European Union	Steel
CrNi18/9-0.03C/N	BS	British	Steel and Flat
X3CrNi18-10	AFNOR NF	France	Steel and Tube
SUS 304 LN	JIS	Japan	Steel, Plate, Sheet and Strip
X2CrNi18-10	UNI	Italy	Sheet, Plate, Strip and Bar
X2CrNi18 10 KKW	ONORM	Austria	Steel

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com