

## Material: BS 2875 CZ 120

### Standard Specification for Copper and Copper Alloys for Plate

**Group:** Non-Ferrous Copper Alloy

**Sub Group:** BS 2875 Copper and Copper Alloys for Plate

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Plate

Chemical Composition			Heat Treatment	
Other	Ot%	0.300 max.	Half Hardening or Hardening or Extra Hardening	
Lead	Pb %	1.500 - 2.500		
Copper	Cu %	58.000 - 60.000		
Zinc	Zn %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	510 - 575
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	3 - 10
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HV	110 - 190
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuZn39 Pb2	IS	India	Strip
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)