

Material: BS B 4

Standard Specification for Steel Castings for General Engineering Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: BS B 4 Steel Castings for General Engineering Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.250 max.	Annealing or Normalizing or Hardening + Tempering	
Silicon	Si %	0.750 max.		
Manganese	Mn %	0.300 - 0.700		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	2.500 - 3.500		
Nickel	Ni %	0.400 max.		
Molybdenum	Mo %	0.350 - 0.600		
Copper	Cu %	0.300 max.		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	620 - 940
-	-	-	Yield Strength in Mpa	370 min.
-	-	-	Elongation in %	10 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	179 - 277
-	-	-	Impact in Joule	10 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J13052	UNS	USA	Casting
200-400 W	JIS	Japan	Casting
B 2	BS	British	Forging
6120	AISI	USA	Forging, Bar, Wire, and Shape
B 5	BS	British	Forging
B 6	BS	British	Forging
A732 5N	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com