

Material: BS EN 1982 CuMn11Al8Fe3Ni3-C (CC212E)

Standard Specification for Copper and Copper Alloys - Ingot and Casting

Group: Non-Ferrous Copper Alloy

Sub Group: BS EN 1982 Standard Specification for Copper and Copper Alloys - Ingot and Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Magnesium	Mg %	0.050 max.	As-Cast	
Lead	Pb %	0.050 max.		
Silicon	Si %	0.100 max.		
Tin	Sn %	0.500 max.		
Zinc	Zn %	1.000 max.		
Nickel	Ni %	1.500 - 4.500		
Iron	Fe %	2.000 - 4.000		
Manganese	Mn %	8.000 - 15.000		
Aluminium	Al %	7.000 - 9.000		
Copper	Cu %	68.000 - 77.000		
-	-	-	Mechanical Properties Tensile Strength in Mpa 630 min. Yield Strength in Mpa 275 min. Elongation in % 18 min. Reduction of Area in % - Hardness in HBW 150 min. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com