

Material: BS EN 1982 CuNi10Fe1Mn1-B (CB380H)

Standard Specification for Copper and Copper Alloys - Ingot and Casting

Group: Non-Ferrous Copper Alloy

Sub Group: BS EN 1982 Standard Specification for Copper and Copper Alloys - Ingot and Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.010 max.	As-Cast	
Copper	Cu %	0.100 max.		
Niobium	Nb %	1.000 max.		
Lead	Pb %	0.030 max.		
Zinc	Zn %	0.500 max.		
Silicon	Si %	0.100 max.		
Manganese	Mn %	1.000 - 1.500		
Iron	Fe %	1.000 - 1.800		
Nickel	Ni %	9.000 - 11.000		
Copper	Cu %	84.500 min.		
-	-	-	Mechanical Properties Tensile Strength in Mpa 280 min. Yield Strength in Mpa 120 min. Elongation in % 20 min. Reduction of Area in % - Hardness in HBW 70 min. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com