

Material: BS EN 1982 CuSn10-C (CC480K)

Standard Specification for Copper and Copper Alloys - Ingot and Casting

Group: Non-Ferrous Copper Alloy

Sub Group: BS EN 1982 Standard Specification for Copper and Copper Alloys - Ingot and Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Nickel	Ni %	2.000 max.	As-Cast	
Phosphorus	P %	0.200 max.		
Lead	Pb %	0.100 max.		
Aluminium	Al %	0.010 max.		
Iron	Fe %	0.200 max.		
Manganese	Mn %	0.100 max.		
Sulphur	S %	0.050 max.		
Antimony	Sb %	0.200 max.		
Zinc	Zn %	0.500 max.		
Tin	Sn %	9.000 - 11.000	Mechanical Properties	
Cu + Ni	Cu%+Ni%	88.000 - 90.000	Tensile Strength in Mpa	250 min.
-	-	-	Yield Strength in Mpa	130 min.
-	-	-	Elongation in %	18 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HBW	70 min.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CB480K	AFNOR NF	France	Ingot and Casting
CB480K	DIN	Germany	Ingot and Casting
CB480K	BDS	Bulgaria	Ingot and Casting
CuSn10-B	ONORM	Australia	Ingot and Casting
CuSn10-B	UNI	Italy	Ingot and Casting
CuSn10-B	MSZ	Hungary	Ingot and Casting
CuSn10-B	UNE	Spain	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com