

Material: BS EN 1982 CuSn5Zn5Pb2-C (CC491K)

Standard Specification for Copper and Copper Alloys - Ingot and Casting

Group: Non-Ferrous Copper Alloy

Sub Group: BS EN 1982 Standard Specification for Copper and Copper Alloys - Ingot and Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.010 max.	As-Cast	
Arsenic	As %	0.030 max.		
Bismuth	Bi %	0.020 max.		
Cadmium	Cd %	0.020 max.		
Chromium	Cr %	0.020 max.		
Iron	Fe %	0.300 max.		
Sulphur	S %	0.040 max.		
Antimony	Sb %	0.100 max.		
Silicon	Si %	0.010 max.		
Nickel	Ni %	0.600 max.		
Phosphorus	P %	0.040 max.	Mechanical Properties	
Lead	Pb %	3.000 max.		
Zinc	Zn %	4.000 - 6.000		
Tin	Sn %	4.000 - 6.000		
Copper	Cu %	84.000 - 88.000		
			Tensile Strength in Mpa	200 min.
			Yield Strength in Mpa	90 min.
			Elongation in %	13 min.
			Reduction of Area in %	-
			Hardness in HBW	60 min.
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CB491K	UNE	Spain	Ingot and Casting
CuSn5Zn5Pb5-B	UNE	Spain	Ingot and Casting
CB491K	CSN	Czech Republic	Ingot and Casting
CuSn5Zn5Pb5-B	CSN	Czech Republic	Ingot and Casting
CB491K	UNI	Italy	Ingot and Casting
CuSn5Zn5Pb5-B	UNI	Italy	Ingot and Casting
CB491K	DIN	Germany	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com