

Material: BS EN 1982 CuSn6Zn4Pb2-B (CB498K)

Standard Specification for Copper and Copper Alloys - Ingot and Casting

Group: Non-Ferrous Copper Alloy

Sub Group: BS EN 1982 Standard Specification for Copper and Copper Alloys - Ingot and Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.010 max.	As-Cast	
Iron	Fe %	0.250 max.		
Sulphur	S %	0.100 max.		
Antimony	Sb %	0.250 max.		
Silicon	Si %	0.010 max.		
Nickel	Ni %	1.000 max.		
Phosphorus	P %	0.050 max.		
Lead	Pb %	1.000 - 2.000	Mechanical Properties Tensile Strength in Mpa 220 min. Yield Strength in Mpa 110 min. Elongation in % 15 min. Reduction of Area in % - Hardness in HBW 65 min. Impact in Joule -	
Zinc	Zn %	3.000 - 5.000		
Tin	Sn %	5.500 - 6.500		
Cu + Ni	Cu%+Ni%	86.000 - 90.000		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com