

Material: BS EN 1982 CuZn39Pb1AlB-C (CC755S)

Standard Specification for Copper and Copper Alloys - Ingot and Casting

Group: Non-Ferrous Copper Alloy

Sub Group: BS EN 1982 Standard Specification for Copper and Copper Alloys - Ingot and Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.400 - 0.700	As-Cast	
Iron	Fe %	0.050 - 0.200		
Lead	Pb %	1.200 - 1.700		
Manganese	Mn %	0.050 max.		
Nickel	Ni %	0.200 max.		
Silicon	Si %	0.050 max.		
Tin	Sn %	0.300 max.		
Copper	Cu %	59.500 - 61.000		
Zinc	Zn %	Balance	Mechanical Properties Tensile Strength in Mpa 350 min. Yield Strength in Mpa 250 min. Elongation in % 4 min. Reduction of Area in % - Hardness in HBW 110 min. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CB755S	DIN	Germany	Ingot and Casting
CB755S	AFNOR NF	France	Ingot and Casting
CB755S	ONORM	Australia	Ingot and Casting
CB755S	MSZ	Hungary	Ingot and Casting
CuZn39Pb1AlB-B	UNI	Italy	Ingot and Casting
CuZn39Pb1AlB-B	CSN	Czech Republic	Ingot and Casting
CuZn39Pb1AlB-B	UNE	Spain	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com