

Material: BSI BS1400 G3-TF CuSn7Ni5Zn3

Standard Specification for Copper Alloy and High Conductivity Conductivity Copper Casting

Group: Non-Ferrous Copper Alloy

Sub Group: BSI BS1400 Copper Alloy and High Conductivity Conductivity Copper Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Tin	Sn %	6.500 - 7.500	As-Cast	
Zinc	Zn %	1.500 - 3.000		
Lead	Pb %	0.100 - 0.500		
Phosphorus	P %	0.020 max.		
Nickel	Ni %	5.250 - 5.750		
Aluminium	Al %	0.010 max.		
Manganese	Mn %	0.200 max.		
Silicon	Si %	0.020 max.		
Bismuth	Bi %	0.020 max.		
Sulphur	S %	0.100 max.		
Other	Ot%	0.500 max.	Mechanical Properties Tensile Strength in Mpa 430 min. Yield Strength in Mpa 280 min. Elongation in % 3 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
Copper	Cu %	Balance		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com