

Material: CSN 422744

Standard Specification for Alloy Steel Casting

Group: Ferrous Mild Steel Alloys

Sub Group: CSN 422744 Alloy Steel Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.110 - 0.190	Normalizing or Annealing or Hardening + Tempering	
Silicon	Si %	0.200 - 0.500		
Manganese	Mn %	0.400 - 0.700		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	0.500 - 0.700		
Nickel	Ni %	0.400 max.		
Molybdenum	Mo %	0.400 - 0.600		
Vanadium	V %	0.200 - 0.350		
P + S	P% + S%	0.060 max.		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 550 - 650 Yield Strength in Mpa 300 min. Elongation in % 16 min. Reduction of Area in % 22 min. Hardness in HB 141 - 183 Impact in Joule 200 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J21610	UNS	USA	Casting
1.7706	EN	European Union	Casting
1.7706	DIN	Germany	Casting
G 17 CrMoV 5-10	AFNOR NF	France	Casting
G 17 CrMoV 5-10	UNI	Italy	Casting
L 17 HMF	PN	Poland	Casting
A356 9	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com