

Material: CSN GX 3 CrNi 13 4

Standard Specification for Steel Castings for Pressure Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: CSN GX 3 CrNi 13 4 Steel Castings for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 max.	Normalizing or Quenching or Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	12.000 - 13.500		
Molybdenum	Mo %	0.700 max.		
Nickel	Ni %	3.500 - 5.000		
Copper	Cu %	0.300 max.		
Vanadium	V %	0.800 max.		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 700 - 900 Yield Strength in Mpa 500 min. Elongation in % 15 min. Reduction of Area in % - Hardness in BHN - Impact in Joule 50 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 10213 GX3CrNi13-4	BS	British	Plate, Tubes and Forging
GX3CrNi13-4	ISO	International	Casting
1.6982	ISO	International	Casting
1.6982	BDS	Bulgaria	Casting
GX 3 CrNi 13 4	BDS	Bulgaria	Casting
1.6982	CSN	Czech Republic	Casting
GX 3 CrNi 13 4	SFS	Finland	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com