

Material: CSN GX2CrNiMoN25-7-3

Standard Specification for Steel Castings for Pressure Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: CSN GX2CrNiMoN25-7-3 Steel Castings for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.030 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	1.500 max.
Phosphorus	P %	0.030 max.
Sulphur	S %	0.020 max.
Chromium	Cr %	24.000 - 26.000
Molybdenum	Mo %	3.000 - 4.000
Nickel	Ni %	6.000 - 8.500
Copper	Cu %	1.000 max.
Nitrogen	N %	0.150 - 0.250
Tungsten	W %	1.000 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-

Heat Treatment
Normalizing or Quenching or Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	650 - 850
Yield Strength in Mpa	480 min.
Elongation in %	22 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	50 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
GX2CrNiMoN25-7-3	BS	British	Plate, Tubes and Forging
GX2CrNiMoN25-7-3	ISO	International	Casting
1.4417	ISO	International	Casting
GX2CrNiMoN25-7-3	BDS	Bulgaria	Casting
1.4417	BDS	Bulgaria	Casting
1.4417	CSN	Czech Republic	Casting
1.4417	EN	European Union	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India