

Material: DIN 1.0487

Standard Specification for Steel Castings for Pressure Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: DIN 1.0487 Steel Castings for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.180 max.	Normalizing or Annealing or Hardening + Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	0.600 - 1.400		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	0.300 max.		
Molybdenum	Mo %	0.080 max.		
Nickel	Ni %	0.300 max.		
Niobium	Nb %	0.030 max.		
Aluminium	Al %	0.020 min.		
			Mechanical Properties	
Copper	Cu %	0.450 max.	Tensile Strength in Mpa	340 - 510
Nitrogen	N %	0.020 max.	Yield Strength in Mpa	205 min.
Iron	Fe %	Balance	Elongation in %	21 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
			Impact in Joule	27 min. @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G18Mo5	UNI	Italy	Steel
StE285	DIN	Germany	Steel
TS 15 CD 2-05	AFNOR NF	France	Steel
1.5422	EN	European Union	Steel
WStE 285	DIN	Germany	Steel
1.0488	DIN	Germany	Steel
1.0486	DIN	Germany	Steel

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com