

Material: DIN 1.1156

Standard Specification for Castings for Constructional Carbon Steel

Group: Ferrous Mild Steel Alloys

Sub Group: DIN 1.1156 Castings for Constructional Carbon Steel

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.200 - 0.280
Silicon	Si %	0.300 - 0.500
Manganese	Mn %	0.500 - 0.800
Phosphorus	P %	0.030 max.
Sulphur	S %	0.030 max.
Chromium	Cr %	0.300 max.
Nitrogen	N %	0.007 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Normalizing + Tempering or Hardening + Tempering

Mechanical Properties
Tensile Strength in Mpa
Yield Strength in Mpa
Elongation in %
Reduction of Area in %
Hardness in BHN
Impact in Joule

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA-352 LCB	ASME	USA	Casting
J03003	UNS	USA	Casting
1.1156	EN	USA	Casting
GC24E	EN	European Union	Casting
A352 LCB	ASTM	USA	Casting
1.0619	DIN	Germany	Casting
1.0619	EN	European Union	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India