

Material: DIN 1.4958

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: DIN 1.4958 Seamless Steel Tubes for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 - 0.080	Solution Annealing	
Silicon	Si %	0.700 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.015 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	19.000 - 22.000		
Nickel	Ni %	30.000 - 32.500		
Titanium	Ti %	0.200 - 0.500		
Niobium	Nb %	0.100 max.		
Ni + Co	Ni% + Co%	30.000 - 32.500		
			Mechanical Properties	
Aluminium	Al %	0.200 - 0.500	Tensile Strength in Mpa	500 - 750
Al + Ti	Al% + Ti%	0.700 max.	Yield Strength in Mpa	170 min.
Cobalt	Co %	0.500 max.	Elongation in %	30 min.
Copper	Cu %	0.500 max.	Reduction of Area in %	-
Iron	Fe %	Balance	Hardness in BHN	-
			Impact in Joule	80 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
10216-5 EN 1.4958(+RA)	BS	British	Tube
1.4958	EN	European Union	Steel
X5NiCrAlTi31 20	DIN	Germany	Steel and Flat
X5NiCrAlTi31 20	EN	European Union	Steel and Flat
X5NiCrAlTi31 20	DIN	Germany	Steel and Flat
1.4959	EN	European Union	Steel
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com