

Material: DIN 1.6220

Standard Specification for Steel Castings for General Engineering Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: DIN 1.6220 Steel Castings for General Engineering Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.170 - 0.230	As Cast or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	1.000 - 1.600		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	0.300 max.		
Molybdenum	Mo %	0.150 max.		
Nickel	Ni %	0.800 max.		
Copper	Cu %	0.300 max.		
Vanadium	V %	0.050 max.		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 480 - 650 Yield Strength in Mpa 300 min. Elongation in % 20 min. Reduction of Area in % - Hardness in BHN - Impact in Joule 50 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
AM2	BS	British	Casting
2074/C3	AS	Australia	Casting
1.622	ONORM	Australia	Casting
1.622	EN	European Union	Casting
1.622	BDS	Bulgaria	Casting
1.622	SS	Sweden	Casting
1.622	UNE	Spain	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com