

Material: DIN 1.6368

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: DIN 1.6368 Seamless Steel Tubes for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel and Flat

Chemical Composition		
Carbon	C %	0.170 max.
Silicon	Si %	0.250 - 0.500
Manganese	Mn %	0.800 - 0.120
Phosphorus	P %	0.025 max.
Sulphur	S %	0.010 max.
Chromium	Cr %	0.300 max.
Molybdenum	Mo %	0.250 - 0.500
Nickel	Ni %	1.000 - 1.300
Niobium	Nb %	0.015 - 0.045
Aluminium	Al %	0.015 min.
Copper	Cu %	0.500 - 0.800
Nitrogen	N %	0.020 max.
Iron	Fe %	Balance
-	-	-
-	-	-

Heat Treatment
Normalizing + Tempering

Mechanical Properties	
Tensile Strength in Mpa	580 - 780
Yield Strength in Mpa	400 min.
Elongation in %	16 min.
Reduction of Area in %	-
Hardness in HB	-
Impact in Joule	27 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.6368	EN	European Union	Steel and Flat
1.6368	DIN	Germany	Steel and Flat
15NiCuMoNb5	DIN	Germany	Steel
15 NiCuMoNb 5 S	DIN	Germany	Steel
1.6369	DIN	Germany	Steel
1.6369	DIN	Germany	Steel
15 NiCuMoNb 5 S	DIN	Germany	Steel

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India