

Material: DIN 1.7383

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: DIN 1.7383 Seamless Steel Tubes for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel and Flat

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 - 0.150	Quenching + Tempering	
Silicon	Si %	0.500 max.		
Manganese	Mn %	0.400 - 0.800		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.025 max.		
Chromium	Cr %	2.000 - 2.500		
Molybdenum	Mo %	0.900 - 1.100		
Copper	Cu %	0.300 max.		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	450 - 680
-	-	-	Yield Strength in Mpa	265 min.
-	-	-	Elongation in %	17 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	27 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
10216-2	BS	British	Steel and Flat
1.7383	EN	European Union	Steel and Flat
11CrMo9-10	AFNOR NF	France	Steel and Flat
11CrMo9-10	BS	British	Steel and Flat
11CrMo9-10	ISO	International	Steel and Tube
11CrMo9-10	UNI	Italy	Steel and Flat
11CrMo9-10	DIN	Germany	Steel and Flat

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com