

Material: DIN 2.2141

Standard Specification For Zinc and Zinc Alloy Castings

Group: Non-Ferrous Zinc Alloys

Sub Group: DIN 2.2141 Zinc and Zinc Alloy Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	3.700 - 4.100	As-Cast	
Copper	Cu %	0.500 - 1.000		
Magnesium	Mg %	0.030 - 0.060		
Lead	Pb %	0.003 max.		
Cadmium	Cd %	0.003 max.		
Tin	Sn %	0.001 max.		
Iron	Fe %	0.020 max.		
Zinc	Zn %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	330 min.
-	-	-	Yield Strength in Mpa	250 min.
-	-	-	Elongation in %	5 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	92 min.
-	-	-	Impact in Joule	58 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
ZP5	DIN	Germany	Casting
Alloy B	BS	British	Casting
G-ZnAl4Cu1	UNI	Italy	Ingot
ZnAl4Cu1	UNE	Spain	Ingot
ZnAl4Cu1	NS	Norway	Ingot
ZnAl4Cu1	SS	Sweden	Ingot
B 240 AC41A	ASTM	USA	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com