

Material: DIN 2.4011

Standard Specification for Refined Nickel Alloy Castings

Group: Non-Ferrous Nickel Alloys

Sub Group: DIN 2.4011 Refined Nickel Alloy Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.015 max.
Manganese	Mn %	0.0005 max.
Phosphorus	P %	0.001 max.
Cobalt	Co %	0.010 max.
Copper	Cu %	0.005 max.
Iron	Fe %	0.020 max.
sulphur	S %	0.0015 max.
Silver	Ag %	0.0005 max.
Arsenic	As %	0.001 max.
Bismuth	Bi %	0.0001 max.
Lead	Pb %	0.0005 max.
Antimony	Sb %	0.0001 max.
Selenium	Se %	0.0002 max.
Tin	Sn %	0.0001 max.
Tantalum	Ta %	0.0005 max.

Chemical Composition		
Tellurium	Te %	0.0001 max.
Titanium	Ti %	0.0001 max.
Zirconium	Zr %	0.001 max.
Ni + Co	Ni% + Co%	99.960 min.
-	-	-
Heat Treatment		
As-Cast or Annealing or Age Hardning		
Mechanical Properties		
Tensile Strength in Mpa	-	
Yield Strength in Mpa	-	
Elongation in %	-	
Reduction of Area in %	-	
Hardness in BHN	-	
Impact in Joule	-	

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
H-Ni99,96	DIN	Germany	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com