

Material: DIN 2.4648

Standard Specification for Nickel and Nickel Alloy Casting

Group: Non-Ferrous Nickel Alloys

Sub Group: DIN 2.4648 Nickel and Nickel Alloy Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.800 max.		
Manganese	Mn %	2.000 - 6.000		
Chromium	Cr %	18.000 - 22.000		
Niobium	Nb %	1.500 - 3.000		
Copper	Cu %	0.500 max.		
Iron	Fe %	4.000 max.		
Molybdenum	Mo %	2.000 max.		
Sulphur	S %	0.015 max.		
Titanium	Ti %	0.500 max.		
Other	Ot%	0.500 max.	Mechanical Properties	
Ni + Co	Ni% + Co%	63.000 min.	Tensile Strength in Mpa	600 min.
-	-	-	Yield Strength in Mpa	360 min.
-	-	-	Elongation in %	25 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	60 @RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
E Ni 6082	ISO	International	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com