

Material: DIN 2.4700

Standard Specification for Nickel-base alloy NiCr21Mo20N Sheet and Strip

Group: Non-Ferrous Nickel Alloys

Sub Group: DIN 2.4700 Nickel-base alloy NiCr21Mo20N Sheet and Strip

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.100 max.		
Manganese	Mn %	0.500 max.		
Chromium	Cr %	20.000 - 23.000		
Cobalt	Co %	0.300 max.		
Aluminium	Al %	0.400 max.		
Iron	Fe %	1.500 max.		
Molybdenum	Mo %	18.500 - 21.000		
Nitrogen	N %	0.020 - 0.150		
Phosphorus	P %	0.015 max.		
			Mechanical Properties	
Sulphur	S %	0.010 max.	Tensile Strength in Mpa	760 min.
Tungsten	W %	0.300 max.	Yield Strength in Mpa	360 min.
Copper	Cu %	0.500 max.	Elongation in %	40 min.
Nickel	Ni %	Balance	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
			Impact in Joule	120 @RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
VDM alloy 2120 MoN	Gravity	India	Sheet and Strip
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com