

Material: DIN 2.4878

Standard Specification for Nickel and Nickel Alloy Casting

Group: Non-Ferrous Nickel Alloys

Sub Group: DIN 2.4878 Nickel and Nickel Alloy Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Chemical Composition		
Carbon	C %	0.030 - 0.070	Zirconium	Zr %	0.030 - 0.070
Silicon	Si %	0.500 max.	Nickel	Ni %	Balance
Manganese	Mn %	0.500 max.	-	-	-
Chromium	Cr %	23.000 - 25.000	-	-	-
Copper	Cu %	0.200 max.	-	-	-
Cobalt	Co %	19.000 - 21.000	Heat Treatment		
Aluminium	Al %	1.200 - 1.600	As-Cast or Annealing or Age Hardning		
Boron	B %	0.010 - 0.015	Mechanical Properties		
Iron	Fe %	1.000 max.	Tensile Strength in Mpa	1080 min.	
Molybdenum	Mo %	1.000 - 2.000	Yield Strength in Mpa	650 min.	
Nb + Ta	Nb% + Ta%	0.700 - 1.200	Elongation in %	12 min.	
Phosphorus	P %	0.010 max.	Reduction of Area in %	-	
Sulphur	S %	0.007 max.	Hardness in BHN	-	
Tantalum	Ta %	0.050 max.	Impact in Joule	-	
Titanium	Ti %	2.800 - 3.200			

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
NiCr25Co20TiMo	DIN	Germany	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com