

Material: DIN 9 NiMn 5

Standard Specification for Low Alloyed NiMn Steel

Group: Ferrous Mild Steel Alloys

Sub Group: DIN 9 NiMn 5 Low Alloyed NiMn Steel

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 - 0.120	Annealing or Normalizing or Hardening + Tempering	
Silicon	Si %	0.050 - 0.150		
Manganese	Mn %	0.800 - 1.200		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	0.200 max.		
Nickel	Ni %	1.000 - 1.300		
Copper	Cu %	0.220 max.		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	485 - 655
-	-	-	Yield Strength in Mpa	275 min.
-	-	-	Elongation in %	22 min.
-	-	-	Reduction of Area in %	22 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA-487 Garde 16A	ASME	USA	Casting
1.6222	DIN	Germany	Steel
1.8932	EN	European Union	Forging
E 460 DD	JIS	Japan	Plate
P 420 NH	EN	European Union	Forging
J31200	UNS	USA	Casting
A487 16A	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com