

Material: DIN EN 1982 CB755S

Standard Specification for Copper and Copper Alloys - Ingots and Castings

Group: Non-Ferrous Copper Alloy

Sub Group: DIN EN 1982 Copper and Copper Alloys - Ingots and Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.400 - 0.650	As-Cast	
Iron	Fe %	0.050 - 0.200		
Manganese	Mn %	0.050 max.		
Nickel	Ni %	0.200 max.		
Lead	Pb %	1.200 - 1.700		
Silicon	Si %	0.030 max.		
Tin	Sn %	0.300 max.		
Copper	Cu %	59.000 - 60.500		
Zinc	Zn %	Balance	Mechanical Properties	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Tensile Strength in Mpa	-
			Yield Strength in Mpa	-
			Elongation in %	-
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CC755S	BS	British	Ingot and Casting
CB755S	AFNOR NF	France	Ingot and Casting
CB755S	ONORM	Australia	Ingot and Casting
CB755S	MSZ	Hungary	Ingot and Casting
CuZn39Pb1AIB-B	UNI	Italy	Ingot and Casting
CuZn39Pb1AIB-B	CSN	Czech Republic	Ingot and Casting
CuZn39Pb1AIB-B	UNE	Spain	Ingot and Casting

Disclaimer: **All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.**

Customer Care: +91-99090 45075 Email: info@icastllp.com