

Material: DIN G 19 NiCrMo 12 6

Standard Specification for Heat treatable alloyed NiCrMo steel

Group: Ferrous Mild Steel Alloys

Sub Group: DIN G 19 NiCrMo 12 6 Heat treatable alloyed NiCrMo steel

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.220 max.	Normalizing or Annealing or Hardening + Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	1.350 - 1.850		
Molybdenum	Mo %	0.350 - 0.600		
Nickel	Ni %	2.500 - 3.500		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	620 min.
-	-	-	Yield Strength in Mpa	450 min.
-	-	-	Elongation in %	22 min.
-	-	-	Reduction of Area in %	40 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	41 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.6783	EN	European Union	Casting
1.6783	DIN	Germany	Casting
UNS J42220	UNS	USA	Casting
G19 NiCrMo 12-6	EN	European Union	Casting
A757 Grade E1Q	ASTM	USA	Casting
A757 Grade E2N1, E2Q1	ASTM	USA	Casting
A757 Grade E2N1, E2Q2	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com