

Material: DIN G-NiCu30Nb

Standard Specification for Nickel and Nickel-Copper Alloy Casting

Group: Non-Ferrous Nickel Alloys

Sub Group: DIN G-NiCu30Nb Nickel and Nickel-Copper Alloy Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.150 max.
Silicon	Si %	0.500 - 1.500
Manganese	Mn %	0.500 - 1.500
Copper	Cu %	26.000 - 33.000
Iron	Fe %	1.000 - 2.500
Aluminium	Al %	0.500 max.
Magnesium	Mg %	0.120 max.
sulphur	S %	0.010 max.
Titanium	Ti %	0.200 max.
Niobium	Nb %	1.000 - 1.500
Lead	Pb %	0.010 max.
Other	Ot%	1.000 max.
Ni + Co	Ni% + Co%	62.000 - 68.000
-	-	-
-	-	-

Heat Treatment	
As-Cast or Annealing or Age Hardning	

Mechanical Properties	
Tensile Strength in Mpa	450 min.
Yield Strength in Mpa	220 min.
Elongation in %	25 min.
Reduction of Area in %	-
Hardness in BHN	120 min.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
2.4365	DIN	Germany	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com