

Material: DIN GX12CrMoVNbN9-1

Standard Specification for Steel Castings for Pressure Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: DIN GX12CrMoVNbN9-1 Steel Castings for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 - 0.140	Normalizing or Quenching or Solution Annealing	
Silicon	Si %	0.200 - 0.500		
Manganese	Mn %	0.300 - 0.800		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	8.000 - 9.500		
Molybdenum	Mo %	0.850 - 1.050		
Nickel	Ni %	0.400 max.		
Nitrogen	N %	0.030 - 0.070		
Vanadium	V %	0.180 - 0.250		
			Mechanical Properties	
Niobium	Nb %	0.060 - 0.100	Tensile Strength in Mpa	600 - 750
Aluminium	Al %	0.020 max.	Yield Strength in Mpa	460 min.
Iron	Fe %	Balance	Elongation in %	15 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	27 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
GX12CrMoVNbN9-1	BS	British	Plate, Tubes and Forging
GX12CrMoVNbN9-1	ONORM	Australia	Casting
GX12CrMoVNbN9-1	NBN	Belgium	Casting
GX12CrMoVNbN9-1	BDS	Bulgaria	Casting
GX12CrMoVNbN9-1	CSN	Czech Republic	Casting
GX12CrMoVNbN9-1	EN	European Union	Casting
GX12CrMoVNbN9-1	SFS	Finland	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com