

Material: DIN GX2CrNiMoN26-7-4

Standard Specification for Austenitic-Ferritic Steel; Corrosion Resistant Steel Castings

Group: Ferrous Stainless Steel Alloys

Sub Group: DIN GX2CrNiMoN26-7-4 Austenitic-Ferritic Steel; Corrosion Resistant Steel Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.025 max.		
Chromium	Cr %	25.000 - 27.000		
Nickel	Ni %	6.000 - 8.000		
Molybdenum	Mo %	3.000 - 5.000		
Nitrogen	N %	0.120 - 0.220		
Copper	Cu %	1.300 max.		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 650 - 850 Yield Strength in Mpa 480 min. Elongation in % 22 min. Reduction of Area in % - Hardness in BHN - Impact in Joule 50 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4469	EN	European Union	0
GX2CrNiMoN26-7-4	AFNOR NF	France	Casting
GX2CrNiMoN25-7-4	DIN	Germany	Casting
J93404	UNS	USA	Casting
1.4469	EN	European Union	Casting
A995 5A	ASTM	USA	Casting
A890 5A	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com