

Material: DIN NiCo 15 Cr 15 MoAlTi

Standard Specification for NiCrCoMoTiAl Alloy Casting

Group: Non-Ferrous Nickel Alloys

Sub Group: DIN NiCo 15 Cr 15 MoAlTi NiCrCoMoTiAl Alloy Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.120 - 0.200	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	14.000 - 16.000		
Aluminium	Al %	4.500 - 5.500		
Copper	Cu %	0.200 max.		
Cobalt	Co %	13.000 - 17.000		
Boron	B %	0.010 - 0.025		
Iron	Fe %	1.000 max.		
Molybdenum	Mo %	3.000 - 5.000	Mechanical Properties	
Phosphorus	P %	0.045 max.	Tensile Strength in Mpa	-
Sulphur	S %	0.030 max.	Yield Strength in Mpa	-
Titanium	Ti %	3.500 - 4.500	Elongation in %	-
Zirconium	Zr %	0.250 max.	Reduction of Area in %	-
Nickel	Ni %	Balance	Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
2.4636	DIN	Germany	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com